## PL984



PROPERTY	DESCRIPTION		
Primary/Stalk Yarn Type:	Polypropylene		
Secondary/Thatch Yarn Type:	N/A		
Yarn Cross Section:	Texturized Polypropylene		
Standard Color(s)*:	Field/Apple		
UV Stabilized:	Yes		
Fabric Construction:	Tufted		
Primary Backing:	ArmorLoc <sup>™</sup> 3L Stabilized Woven PP/PET Multilayer		
Coating Type(s):	SilverBack <sup>TM</sup> Polyurethane		
Perforations:	Optional		
Yarn Denier/Ends:	4600/8		
Pile Height:	1"		
Face Weight:	35 oz/yd²		
Fabric Width:	15 ft.		



## **APPLICATION**

Designed specifically for golf applications, PL984 features a textured polypropylene profile ideal for putting greens and pitching surfaces. The realistic field and apple-colored grass fibers create a natural look, and the low-maintenance surface performs well both indoors and outdoors. It can be installed on concrete or a compacted aggregate base.









## PL984

FINISHED FABRIC	ENGLISH SYSTEM		METRIC SYSTEM		ASTM TEST F-1551
Nominal Specification	Value	Units	Value	Units	Method
Pile Height (Nominal)	1	ln.	25.4	mm.	D-5823
Face Weight	35	oz/yd²	1,187	g/m²	D-5848
Total Fabric Weight	62	oz/yd²	2,102	g/m²	D-5848
Primary Backing Weight	7	oz/yd²	237	g/m²	D-5848
Secondary Coating Weight	20	oz/yd²	678	g/m²	D-5848
Tuft Bind	>8	lbs.	>3.6	Kg.	D-1335
Grab Tear Strength (Average)	>200	lbs.	>91	Kg.	D-5034
Lead Content	<50	ppm	<50	ppm	F-2765
Total Yarn Linear Density	4,600	Denier	5,111	D-Tex	D-1577
Tensile Strength	8	lbs.	3.6	Kg.	D-5034
Stitch Rate	15.25	Per 3"	20	Per 10 cm	D-5793
Machine Gauge	3/8"	ln.	.95	Cm.	D-5793
Flammability	TEST	PASSED	TEST	PASSED	D-2859
Water Permeability with Infill, Perforated	>30	In./Hr.	>76	Cm./Hr.	F-1551
Fiber Thickness	-	_	100	microns	None



