


# PL705



Standard Line and Field Colors\*



## PROPERTY

## DESCRIPTION

Primary Yarn Polymer	Polypropylene
Yarn Cross Section	Texturized Polypropylene
Standard Colors	Pine; Viridian
Colors Available	Clay; White; Fla Blue; Orange; Yellow; Red; Black
Coating Type(s)	5mm Polyurethane Foam/ SilverBack™
Perforations	No
Pile Height	9/16"
Total Fabric Weight	118 oz/yd <sup>2</sup>
Fabric Width	12 ft.
Yarn Shape	



Texturized



## APPLICATION

One of our most popular and versatile surfaces. No infill needed, making it ideal for indoor and portable applications. This product can be installed indoors or outdoors on concrete or a compacted aggregate base.



\*Custom colors available upon request

200 Howell Dr. Dalton GA 30721

[www.cpturf.com](http://www.cpturf.com)

800.564.4492




CONTROLLED  
PRODUCTS




# PL705

FINISHED FABRIC	ENGLISH SYSTEM		METRIC SYSTEM		ASTM TEST F-1551
<b>Nominal Specification</b>	Value	Units	Value	Units	<b>Method</b>
Pile Height (Nominal)	.5625	In.	14.29	mm.	D-5823
Face Weight	36	oz/yd <sup>2</sup>	1221	g/m <sup>2</sup>	D-5828
Total Fabric Weight (SilverBack™)	63	oz/yd <sup>2</sup>	2136	g/m <sup>2</sup>	D-5828
Total Fabric Weight (Greenback)	71	oz/yd <sup>2</sup>	2407	g/m <sup>2</sup>	D-5828
Total Fabric Weight (5mm Foam)	118	oz/yd <sup>2</sup>	4000	g/m <sup>2</sup>	D-5828
Primary backing Weight	7	oz/yd <sup>2</sup>	237	g/m <sup>2</sup>	D-5828
Secondary Weight (SilverBack™)	20	oz/yd <sup>2</sup>	678	g/m <sup>2</sup>	D-5828
Secondary Weight (Greenback)	28	oz/yd <sup>2</sup>	949	g/m <sup>2</sup>	D-5848
Secondary Weight (5mm Foam)	78	oz/yd <sup>2</sup>	2645	g/m <sup>2</sup>	D-5848
Tuft Bind	>8	lbs.	>3.6	Kg.	D-1335
Grab Tear Strength (Average)	>200	lbs.	>91	Kg.	D-2256
Lead Content	<50	ppm	<50	ppm	D-2766
Total Yarn Linear Density	4,600	Denier	5,111	D-Tex	D-1577
Tensile Strength	8.0	lbs.	3.63	Kg.	D-5034
Stitch Rate	18	Per 3"	45.72	Per 10 cm	D-5793
Machine Gauge	0.1875	In.	0.48	Cm.	D-5793
Flammability	TEST	PASSED	TEST	PASSED	D-2859
Water Permeability w/infill	>30	In./Hr.	>76	Cm./Hr.	F-1551
Fiber Thickness	3.9	mils	100	microns	D-3218
Fabric Width	12	Ft.	3.66	M	None



CURB



EQUIPMENT